

# FlexiFlor® Initial Cleaning and Maintenance Procedures

visit [www.FlexiFlor.com](http://www.FlexiFlor.com) for further information

## NO APPLIED FINISHES OR SEALERS ARE REQUIRED

It is recommended that no floor finishes or sealers be used on our rubber flooring material. Gloss level will depend on the frequency of buffing.

### STEP 1

#### Stripping as Needed

**New Rubber Flooring** should be thoroughly machine stripped and scrubbed with a scrubbing pad and stripper. Use stripper manufacturer's recommended stripping procedure.

#### General Cleaning

Clean floor thoroughly with a good grade of mild detergent cleaner. Use cleaner manufacturer's recommended cleaning procedure.

### STEP 2

Neutralize stripper or cleaner with minimum 10% solution of liquid chlorine bleach. Vacuum, mop or squeegee the neutralized solution from the floors. Rinse the floor surface with a solution of 10% liquid chlorine bleach in warm water (may need two or more rinses).

### STEP 3

Once the floor is dry, buff floor using an **Ultra High Speed Buffer** with a red pad. (A light mist of clear water ahead of buffer often helps to develop sheen) After sheen is developed, a higher gloss may be obtained by using a white super polishing pad.

*Note: New Rubber Flooring will require more frequent buffing until a high sheen is acquired.*

### STEP 4

Dry dust or mop floors. Do not use dusters or mops treated with mineral oil or other petroleum products.

### STEP 5

Periodically mop floors using 5% solution of liquid chlorine bleach in water or comparable disinfectant.

## ALL ABOVE STEPS TO BE USED AS NEEDED